

## TECHNICAL DATA SHEET

### PHOS-PREP® PP935 MULTIMETAL ACIDIC DESCALER

#### GENERAL

PHOS-PREP® PP 935 is an acidic cleaner and deoxidiser system designed to ensure a completely clean surface on aluminium, zinc, or steel surfaces before chemical pre-treatment and painting/powder coating. It has been specially formulated to remove scale and white rust.

#### OPERATION

For the make up of a new bath, fill the tank two thirds full with water and add the required volume of PHOS-PREP® PP935. The addition should be made slowly, as heat may be generated during the mixing of the acids with water.

The typical strength of a working bath is between 2 and 10% PHOS-PREP® PP935. Additions are made to the bath to maintain its acidity during operation, and thereby the consistency of its performance. The additions needed are determined by a simple laboratory control method.

PHOS-PREP® PP935 is operated at temperatures between ambient and 60°C, in spray systems or with air agitation to improve the efficiency of operation. The time of processing should be sufficient to produce a completely clean surface, normally between 1 and 5 minutes in most cases. The PHOS-PREP® PP935 stage should be followed by thorough rinsing with clean water.

#### LABORATORY CONTROL

To a 10ml sample of the PHOS-PREP® PP935 bath add 50ml of deionised water and phenolphthalein indicator. Titrate with normal sodium hydroxide solution to a pink end point.

$$\% \text{ vol/vol PHOS-PREP® PP935} = \text{Titre} \div 2$$

The working bath should be maintained at the required strength by the addition of PHOS-PREP® PP 935 concentrate. Addition of 10 litres PHOS-PREP® PP935 concentrate per 1000 litres bath volume will increase the concentration by 1% vol/vol.

#### EQUIPMENT

All tanks and pipe work for use with PHOS-PREP® PP935 should be constructed from stainless steel grade 316 or other acid resistant material.

091017